Modular Drainage System Long Term Load Fatigue





| Test date: | 16/04/24 | Machine: | SiPlan 100 kN fatigue machine | Temperature: | 23.0 °C |
|------------|-------------------|---------------------|-------------------------------|--------------|------------------|
| Tester: | CDM | Strain measurement: | Crosshead | Humidity: | 50.0 % RH |
| Vernier: | Digital (M54, 74) | Test frequency: | 2 Hz | Load levels: | -0.2 kN to -2 kN |

| Height | | | | - | Data | 0 | 0 | |
|--|-------|-------|--------|----------|------------|---------------------|--|--|
| 1 | 2 | 3 | Avg. | Time | Date | Comment | Graph | |
| 100.08 | 100.6 | 99.36 | 100.01 | | 16/04/2024 | | C10F-4 Part 1 Cycles 254 | |
| 98.07 | 98.44 | 95.86 | 97.46 | 10:06:00 | 16/04/2024 | After test | | |
| 98.79 | 98.74 | 99.11 | 98.88 | 10:37:00 | 16/04/2024 | After relax | | |
| 98.36 | 98.36 | 98.78 | 98.5 | 10:43:00 | 16/04/2024 | After test | C10F-4 Part 2 Cycles 255 | |
| 98.98 | 98.6 | 99.44 | 99.01 | 11:15:00 | 16/04/2024 | After relax | | |
| 97.45 | 97.72 | 98.21 | 97.79 | 12:12:00 | 16/04/2024 | After test | C10F-4 Part 3 | |
| 98.49 | 98.52 | 98.89 | 98.63 | 12:46:00 | 16/04/2024 | After relax | Cycles 6506 | |
| Machine cut out outside working hours after 131,673 cycles | | | | 07:15:00 | 17/04/2024 | | No 'After test' measure recorded for Part 4 | |
| 97.75 | 96.66 | 97.12 | 97.18 | 08:15:00 | 17/04/2024 | After relax | Cycles 131,673 | |
| 96.14 | 95.87 | 96.76 | 96.26 | 15:51:00 | 17/04/2024 | After test | C10F-4 Part 5 | |
| 97.43 | 97.12 | 97.26 | 97.27 | 16:21:00 | 17/04/2024 | After relax | Cycles 54,001 | |
| 95.79 | 95.69 | 95.65 | 95.71 | 11:55:00 | 19/04/2024 | After test | C10F-4 Part 6 Cycles 313, 321 | |
| 96.24 | 95.93 | 96.09 | 96.09 | 12:25:00 | 19/04/2024 | After relax | | |
| 97.34 | 96.73 | 97.32 | 97.13 | 09:50:00 | 22/04/2024 | After long relax | | |
| 97.79 | 97.42 | 97.02 | 97.41 | 08:45:00 | 25/04/2024 | After long relax | | |
| | | | | | | | Total Cycles 506,010 | |

Design Life Analysis:

Expected Design Life: 60 years

(Based on known lateral forces within the active load zone and or 6ft drainage, under cycle loading across a range of 50kPa to 95kPa)

Area Calculation for a Diameter of 114.32 mm:

Diameter: 0.11432 m
 Radius: 0.05716 m

Area of Circle: 0.010264 m²

Pressure Calculation for a Load of 2.0 kN:

• Force (F): 2.0 kN × 1,000 = 2,000 N

Pressure (P): 2,000 N / 0.010264 m² ≈ 194.93 kPa

 $\textbf{Deflection:} \ \text{No greater than 5\%}$

(Based on a safety factor range from 2x to 3.8x depending upon loading)







